

Test Summary KATUN STANDARD LIFE DRUM TEST

Test Designator: HP LJ-1320
 DRUM: KATUN STANDARD LIFE
 TONER: KATUN PERFORMANCE
 PURPOSE: SYSTEM TEST
 KATUN DRUM P/N: 35159

DATE: 3/6/2008
 TEMP: 23°C
 RH: 50± 5
 PRINTER: HEWLETT PACKARD LJ-1320
 CARTRIDGE: OEM - Virgin

Image Quality

Section Averages	Density	Background	Character Quality	Vertical Res.	Horizontal Res.
OEM N/N	1.44	0.005%	8.2	62.0	55.5
Test N/N	1.41	0.044%	8.5	68.0	61.5


Toner Consumption

Test Section	Toner Consumed (g)	mg/Print	Toner Transferred (g)	%Transfer	%Waste	Waste Toner (g)	Copies per Ctg./Btl.	Copies in Section
OEM N/N	97.2	32.4	86.6	89.1%	10.9%	10.6	8951	3000
Test N/N	101.6	33.9	93.8	92.3%	7.7%	7.8	8555	3000


OPC Coating Loss

Drum Type	Drum Serial #	Total Copies Run	Coating Thickness at Install	Coating Thickness at End	Total Coating Loss	Loss Per 1K copies	Failure mode
OEM N/N	n/a	3,000	34.2	33.9	0.3	0.100	End of Test
Test N/N	n/a	3,000	33.6	33	0.6	0.200	End of Test

Black Page Image Density



Half-tone Reproductions



Background

